



TECHNICAL DATA

Revised Date: 01/2008
Replaces Date: 07/2005

URA-SHIELD 5324 FAST-CURE AROMATIC URETHANE

Product Description

A 100% solids, rapid cure, two component modified polyurethane. It forms a tough, flexible, impact resistant, seamless, "plastic-like" protection to a variety of substrates. Applied using heated plural component spray equipment.

Features

- Low odor.
- Zero VOC.
- Fast curing for increased productivity.
- Tile-like finish for easy cleanability.
- Resists moisture and various chemicals.
- Meets NSF/ANSI Standard 51 for Food Equipment Materials.

Recommended Uses

As a hard, durable, "plastic-like" protection finish over wood, insulation, dry wall, masonry, plastic and metal to provide an aesthetically pleasing smooth or textured appearance. Typically used for the protection of walls and ceilings in Food Processing and Agriculture facilities, Truck Trailer interiors, Urethane Foam, EPS, Phenolic Foam, and Polystyrene Foam. May be topcoated with Ultrachrome 452 for improved color retention in weathering exposures.

Primers

Steel: FUTURA-BOND 610 HS.
Concrete: FUTURA-BOND 415.
Other: Contact ITW Futura Coatings for recommendations.

Typical Properties

Solids by Volume	99% ±1
Volatile Organic Compounds	0.01 lb/gal (1.5 g/l)
Theoretical Coverage	1604 ft ² @ 1 mil (3.8 m ² @ 1 mm)
Recommend DFT	30 – 100 mils (0.75 – 2.5 mm)
Number of Coats Do not exceed 30 mils/coat	1 to 3
Mix Ratio (by volume)	1"A" : 1"B"
Flash Point (PMCC)	>300°F (149°C)
Shelf Life @ 60-110°F (16-43°C)	12 months
Color	Tint Base *

* White, Black and Green colorant available and is added at time of application.

Specification Data

Elongation – ASTM D 412	30 % (min)
Tensile Strength – ASTM D 412	2400 psi
Hardness – ASTM D 2240	70 Shore "D"
Flexural Modulus - ASTM D 790	64,000
Water Absorption – ASTM 471 3 days @ 75°F	1.1%

Ordering Information

Packaging:	110 gal kits *
Shipping Weight:	10.2 lb/gal (4.6 kg/gal)

* Part A = 55 gallons, Part B = 50 gallons, Colorant = 5 gallons (colorant added to part "B" at time of application).

APPLICATION INFORMATION

URA-SHIELD 5324

Surface Preparation

Remove all oil, grease or other contaminants from the surface to be coated in accordance with SSPC-SP 1.

Steel: Apply over clean, dry, properly applied FUTURA-BOND 610 HS or other recommended primer.

Concrete: Apply over clean, dry, properly applied FUTURA-BOND 415 or other recommended primer. Note: Rough concrete may require surfacing with FUTURA-BOND 320 Gel prior to the application of the FUTURA-BOND 415.

Other: Contact ITW Futura Coatings for specific surface preparation and primer recommendations.

Mixing

Power mix both the "B" component and the colorant to a uniform consistency then add the 5 gallons of colorant to the part "B" component and power mix to a uniform consistency, "A" component does not require mixing.

DO NOT APPLY THE MATERIAL IF THE COLORANT HAS NOT BEEN ADDED TO THE PART "B"
DO NOT BATCH MIX.

Thinning

DO NOT THIN

Pot Life

Material Temperature	Time
75°F (24°C)	< 15 seconds

Application Conditions

	Normal	Minimum	Maximum
Material*	135-150°F (57-65°C)	135°F (57°C)	170°F (77°C)
Surface	75-90°F (24-32°C)	45°F (7°C)	110°F (43°C)
Ambient	75-90°F (24-32°C)	45°F (7°C)	110°F (43°C)
Humidity	30-50%	0%	85%

*Materials **must** be preheated to 70-90°F (21-32°C) prior to use. Surface temperature must be 5°F (3°C) above the dew point.

Application Equipment

Heated Plural Component Airless (only)

Applicator training is required and spray equipment must be approved by ITW Futura Coatings Technical Service.

- 1:1 ratio capable of producing a minimum delivery rate of 1¼ gallons per minute at a tip pressure of 2500-3000 psi.
- Proportioner heaters and heated hose capable of maintaining material temperatures of 135-150°F (57-65°C) at the spray tip.
- Drum heaters capable of maintaining material temperatures of 75-90°F (24-32°C) during application
- 2:1 ratio transfer pumps minimum.
- Contact ITW Futura Coatings for specific information.

Cure Time

These times are based on a 30-50% RH. Excessive film thickness, cooler temperatures or inadequate ventilation will require longer cure times and could result in premature failure.

	<u>Surface Temperature</u>		
	50-69°F (10-21°C)	70-89°F (21-32°C)	90-110°F (32-43°C)
Surface dry	3-5 minutes	2-2 ½ minutes	1-1 ½ minutes
Hard Film	25 minutes	15 minutes	10 minutes
Recoat (min)	5 minutes	5 minutes	5 minutes
Recoat (max)	36 hours	24 hours	12 hours
Full cure	7 days	5 days	3 days

- If the material has exceeded its maximum recoat time by less than 24 hours wipe with MEK and recoat within 10 minutes.
- If the maximum recoat time has been exceeded by more than 24 hours consult ITW Futura Coatings for recommended recoat procedures.

Clean Up

Consult ITW Futura Coatings "Plural Component Equipment Guide" for specific information.

Safety Information

- Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information.
- Do not apply material in enclosed areas without adequate air exchange and ventilation.
- All application personnel must use fresh air respirators or fresh air hoods.
- Wear protective clothing, gloves and eye protection.
- Breathing fumes or contact with the skin may cause severe allergic reactions.
- **This product is intended for industrial use by properly trained professional applicators only.**

Storage Conditions

- Urethane coatings need to be protected from moisture contamination. Store drums and pails in a dry location at 60-90°F (16-32°C).
- Drums **must** be kept sealed at all times with a positive feed dry air, nitrogen blanket or desiccant cartridge system.
- Materials **must** be kept above 50°F (10°C).

ITW FUTURA COATINGS, 1685 GALT INDUSTRIAL BLVD., ST LOUIS, MO, (314) 733-1110

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact ITW Futura Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to ITW Futura quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ITW FUTURA, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.